

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁵ : A61B 17/16, A61C 3/02	A1	(11) International Publication Number: WO 93/24061
		(43) International Publication Date: 9 December 1993 (09.12.93)

(21) International Application Number: PCT/SE93/00452

(22) International Filing Date: 19 May 1993 (19.05.93)

(30) Priority data:
9201670-8 27 May 1992 (27.05.92) SE

(71) Applicant (for all designated States except US): AKTIEBO-
LAGET ASTRA [SE/SE]; S-151 85 Södertälje (SE).

(72) Inventors; and

(75) Inventors/Applicants (for US only): BERGSTRÖM, Nils,
Gustaf [SE/SE]; Avägen 4, S-610 70 Vagnhärad (SE).
HOLMEN, Anders [SE/SE]; Doktorsvägen 7, S-436 50
Hovås (SE).

(74) Agents: KALLING, Sven et al.; AB Astra, Patent Depart-
ment, S-151 85 Södertälje (SE).

(81) Designated States: AT, AU, BB, BG, BR, CA, CH, CZ,
DE, DK, ES, FI, GB, HU, JP, KP, KR, KZ, LK, LU,
MG, MN, MW, NL, NO, NZ, PL, PT, RO, RU, SD, SE,
SK, UA, US, VN, European patent (AT, BE, CH, DE,
DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE),
OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML,
MR, NE, SN, TD, TG).


Published

With international search report.

(54) Title: MÉTHOD OF TREATING SURGICAL DRILL, SURGICAL DRILL AND USE OF SURGICAL DRILL

(57) Abstract

The invention relates to a surgical drill made of metal, for instance made of surgi-
cal grade stainless steel or carbon steel, intended for use when implanting cylindrical
implants into bone tissue, preferably dental implants made of titanium. The body (3) of
the drill (1) is coated by a thin layer of titanium nitride (TiN). The layer of titanium ni-
tride is brightly coloured and circumferential bands (8, 9, 10, 11) having a darker colour
have been etched around the envelope surface of the body (3) of the drill, said bands (8,
9, 10, 11) being located at predetermined distances from each other and having prede-
termined widths.



FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	FR	France	MR	Mauritania
AU	Australia	GA	Gabon	MW	Malawi
BB	Barbados	GB	United Kingdom	NL	Netherlands
BE	Belgium	GN	Guinea	NO	Norway
BF	Burkina Faso	GR	Greece	NZ	New Zealand
BG	Bulgaria	HU	Hungary	PL	Poland
BJ	Benin	IE	Ireland	PT	Portugal
BR	Brazil	IT	Italy	RO	Romania
CA	Canada	JP	Japan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SK	Slovak Republic
CI	Côte d'Ivoire	LJ	Liechtenstein	SN	Senegal
CM	Cameroon	LK	Sri Lanka	SU	Soviet Union
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	MC	Monaco	TG	Togo
DE	Germany	MG	Madagascar	UA	Ukraine
DK	Denmark	ML	Mali	US	United States of America
ES	Spain	MN	Mongolia	VN	Viet Nam
FI	Finland				

METHOD OF TREATING SURGICAL DRILL, SURGICAL DRILL AND
USE OF SURGICAL DRILL

5

Technical field of the invention

10 The invention relates to surgical drills made of metal,
for instance made of surgical grade stainless steel,
which are intended for use when implanting cylindrical
implants into bone tissue, preferably dental implants
made of titanium. The invention also relates to a
method for treating such drills and to the use of such
15 drills.

Background of the invention

20 When implants are fitted into bone tissue, different
kinds of metallic surgical tools are used to prepare
the site in the tissue where the implant is to be
located. These tools normally are made of carbon steel
(normally in disposable tools) or surgical grade
stainless steel (normally in non-disposable tools).

25

In some cases it may however be advantageous if at
least the surface of the tools are covered with a
material which is more biocompatible than the
material in the tool even if the tool is not to remain
30 in the bone tissue for a long period of time. This
material of course should be equally hard or harder
than the material in the tool. This is particularly
advantageous in drills. Drills will be in a close
contact with the tissue during a relatively long period
35 of time since their sides are in rotary contact with
the sides of the borehole during the entire time the
front part of the drill is cutting through the bone

tissue. If the drill is not of an inert material as regards the chemical environment prevalent in bone tissue and blood, some slight contaminations may affect the sides of the bore hole. These contaminants can
5 affect the so-called osseointegration process which is important in connection with bone implants and which seems to be sensitive in respect of contaminants.

Another prerequisite for a good osseointegration is a
10 good, stable fit between bone tissue and implants, the osseointegration being dependent on a close contact between bone tissue and implant surface. When a bore-hole for an implant is drilled, it therefore is
15 important that the length of the bore-hole corresponds as closely as possible to the length of the implant chosen.

It is also very important that the bore-holes are drilled to an exact, pre-determined depth in the parts
20 of the jaw where the nerve is located in order to avoid damage to the nerve.

Brief description of the inventive concept

25 The above problems are solved in that a drill of the kind described introductorily is coated by a thin, brightly coloured layer of titanium nitride (TiN). Titanium nitride has a higher level of biocompatibility than the materials normally used in surgical drills.

30 In a preferred embodiment circumferential band(s) having a darker colour have been etched in the brightly coloured layer of titanium nitride around the envelope surface of the drill. Said bands are located at pre-
35 determined distances from each other and have pre-determined widths.

Further advantageous embodiments and a use of a drill according to the invention are set forth in the dependent claims. A method of obtaining a drill according to the invention is set forth in the independent claim 6.

Brief description of the appended drawing

The only drawing shows a preferred embodiment of a drill according to the invention in a longitudinal side view.

Detailed description of a preferred embodiment of the invention

A drill 1 designed in accordance with the invention is shown in the drawing. The drill is provided with a shank designed with a tang 5 designed in accordance with ISO 1797. The diameter of the drill is etched in the shank, at 7. The drill in this particular case is manufactured of stainless steel W.Nr 1.4034, AISI 420.

The drill 1 further is provided with a fluted body 3 having two helical flutes 4, only one being indicated. The neck between the body and the shank is provided with a coloured band 6 identifying the size of the drill in that each size of drill has a band of a different colour.

The entire length A of the body is covered with a thin layer of titanium nitride having a bright yellow colour.

As indicated by means of the chain of measurements 12, a dark band 8 having a width of 1 mm is located at a distance of 8 mm from the tip of the drill 1. Each following dark band 9, 10, 11 is separated from the

adjacent band by means of a space having a width of exactly 2 mm. Since the titanium nitride has a bright yellow colour and the darker bands are almost black, a very distinct level indication is given at each
5 boundary line between darker bands and lighter areas.

The drill according to the invention can be fabricated in the following steps:

- 10 a) coating the drill with a thin layer of titanium nitride (TiN) by means of chemical vapour deposition until the drill obtains a bright permanent colour,
- b) etching circumferential bands with pre-determined widths being located at pre-determined distances from each other around the outer surface of the drill by
15 means of a laser beam, the bands thus being dark and sharply defined.

The use of a laser beam has the advantage that the boundary lines will be very sharp and well defined and
20 that the contrast between darker and lighter areas will be high.

The etched areas will remain essentially smooth in spite of the treatment, which ensures that there will
25 be no rough areas on the drill upon which contaminants easily will adhere.

When the drill is to be used, for instance in order to implant a screw-shaped fixture for a dental implant,
30 the type of fixture is first chosen in accordance to the prevailing conditions in the jaw, i. e. for instance the shape of the jaw-bone. A drill having a diameter adapted to the diameter of the implant is then chosen and a hole is bored into the jaw-bone. As
35 mentioned above, the drill is provided with dark, circumferential bands corresponding to the lengths of a series of standard sizes of implants having a diameter

- corresponding to the diameter of the drill. The bore-hole is drilled to a depth determined by that boundary between darker band and lighter titanium nitride surface which corresponds to the implant chosen. The fixture is then screwed into the jaw bone. Since the depth of the hole exactly corresponds to the length of the fixture (or of the threaded part thereof), the fixture will fit closely in the hole.
- 10 Bone implants may also be relatively smooth instead of being provided with threads. This kind of implants sometimes are carefully tapped into place in a borehole in the bone by means of a small hammer. The bore-hole may have a diameter which is slightly narrower than the diameter of the implant. However carefully this is done, there always is a risk that the fixture may be pushed to far down into the hole if the length of the hole does not exactly correspond to the fixture. The drill according to the invention thus may be particularly useful in this case, since it may be difficult to extract an implant which has been pushed to far down into a hole.
- 25 These problems might also arise if the bore-hole is to shallow for the implant. In both cases the act of extraction per se might cause a trauma to the walls of the bore-hole which might have a deleterious influence on the osseointegration process.
- 30 If the surface of the bone into which the fixture is to be inserted is obliquely oriented relative to the longitudinal direction of the hole, the above-mentioned boundarys on the drill will also serve as indexes on a ruler for measuring the difference in level between the edges of the bore-hole and will consequently be very useful when determining how deep the hole has to be in order to house the implant correctly in relation to the

oblique surface of the bone.

5 It should be emphasized that the invention is not limited to the embodiment described above and can be varied in many ways within the scope of the appended claims.

10 In particular, the invention should not be considered to be limited to the field of dental implants. The invention thus also is applicable to the entire field of implants in bone tissue.

15 Furthermore, the bore-hole for instance could be bored in two stages a first stage with a narrow pilot drill and a second stage with a full-size drill. It might also be conceivable to provide only one band on the drill body.


CLAIMS

1. Surgical drill made of metal, for instance made of
5 surgical grade stainless steel or carbon steel,
intended for use when implanting cylindrical implants
into bone tissue, preferably dental implants made of
titanium, c h a r a c t e r i z e d in that the body
(3) of said drill (1) is coated by a thin layer of
10 titanium nitride (TiN).
2. Surgical drill according to claim 1 having a
brightly coloured layer of titanium nitride,
c h a r a c t e r i z e d in that circumferential
15 band(s) (8, 9, 10, 11) having a darker colour have been
etched around the envelope surface of the body (3) of
the drill, said bands (8, 9, 10, 11) being located at
pre-determined distances from each other and having
pre-determined widths.
20
3. Surgical drill according to claim 2,
c h a r a c t e r i z e d in that each boundary line
between darker bands and more brightly coloured areas
on the drill corresponds to a specific standard size of
25 implant.
4. Surgical drill according to anyone of claims 2 or 3,
c h a r a c t e r i z e d in that each band (9, 10)
has a width of 2 mm, apart from the band (8) located
30 next to the tip of the drill and the band located next
to the neck of the drill which have a width of 1 mm,
the distance between the edges of each pair of adjacent
bands being 2 mm.
- 35 5. Use of drill according to any one of claims 1 - 4,
comprising the steps of
a) choosing a standard size implant according to the

- prevailing conditions of the bone tissue into which the implant is to be implanted,
- b) drilling a hole for the implant by means of a drill, said drill having a diameter corresponding to the diameter of the chosen implant, to a depth corresponding to the length of the implant, said depth being determined by means of that distinct boundary between darker and lighter areas corresponding to the implant chosen,
- c) inserting the implant.

6. Method for treating surgical bone drills made of metal, for instance surgical grade stainless steel or carbon steel, intended for use when implanting implants into bone tissue, preferably dental implants made of titanium, comprising the steps of
- a) coating the drill with a thin layer of titanium nitride (TiN) by means of chemical vapour deposition until the drill obtains a bright permanent colour,
- b) etching circumferential bands with pre-determined widths and being located at pre-determined distances from each other around the outer surface of the drill by means of a laser beam, the bands thus being dark and sharply defined.

- 1 / 1 -



INTERNATIONAL SEARCH REPORT

International application No.

PCT/SE 93/00452

A. CLASSIFICATION OF SUBJECT MATTER

IPC5: A61B 17/16, A61C 3/02

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC5: A61B, A61C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

SE,DK,FI,NO classes as above

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	GB, A, 2203343 (A.A. SNAPER), 19 October 1988 (19.10.88), claims 1,8,14	1
Y	--	2-4,6
P,X	US, A, 5125838 (M. SEIGNEURIN), 30 June 1992 (30.06.92), column 1, paragraph 1	1
X	DE, C1, 3339004 (SCHMIDT, K.-H.), 27 June 1985 (27.06.85), column 2, line 24 - line 26	1
Y	DE, A1, 3622676 (SCHOLZ, W.), 12 March 1987 (12.03.87), figures 1-3, claim 1	2-4

☒ Further documents are listed in the continuation of Box C.☒ See patent family annex.

* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "B" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

18 August 1993

Date of mailing of the international search report

19 -08- 1993

Name and mailing address of the ISA/
Swedish Patent Office
Box 5055, S-102 42 STOCKHOLM
Facsimile No. +46 8 666 02 86

Authorized officer

Joakim Grip
Telephone No. +46 8 782 25 00

INTERNATIONAL SEARCH REPORT

International application No.

PCT/SE 93/00452

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US, A, 4897037 (D.C. APPLEBY), 30 January 1990 (30.01.90), column 2, line 62 - column 3, line 2, detail 20, 22 --	2,6
A	CH, A5, 588854 (FIRMA GEROLD SCHENKER), 15 June 1977 (15.06.77) --	1-4,6
A	CH, A5, 614372 (PFAUDLER-WERKE AG), 30 November 1979 (30.11.79) -- -----	1-4,6

INTERNATIONAL SEARCH REPORT
Information on patent family members

02/07/93

International application No.
PCT/SE 93/00452

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
GB-A-	2203343	19/10/88	US-A- 4681541	21/07/87
US-A-	5125838	30/06/92	EP-A- 0402293	12/12/90
DE-C1-	3339004	27/06/85	NONE	
DE-A1-	3622676	12/03/87	NONE	
US-A-	4897037	30/01/90	NONE	
CH-A5-	588854	15/06/77	NONE	
CH-A5-	614372	30/11/79	BE-A- 852131	05/09/77
			DE-A,B,C 2621384	17/11/77
			FR-A,B- 2350824	09/12/77
			GB-A- 1559212	16/01/80
			JP-C- 1334390	28/08/86
			JP-A- 53004396	14/01/78
			LU-A- 77323	24/08/77
			NL-A- 7704139	16/11/77
			US-A- 4177524	11/12/79